

Supplemental Table 2 Nanoparticle characterizations in MQ and FW

A Hydrodynamic Diameters of the NPs in different media

Nanoparticle	DLS-MQ	DLS-FW	Zeta-MQ	Zeta-FW
Ag/Si 70/20-0x	125.22 (\pm 0.8)	122.31 (\pm 0.25)	-19.45 (\pm 1.2)	-26.76 (\pm 2.57)
Ag/Si 70/20-1x	197.1 (\pm 0.6)	199.0 (\pm 1.0)	42.8 (\pm 0.8)	16.6 (\pm 0.5)
Si 80-0x	101.13 (\pm 0.11)	101.17 (\pm 9.93)	-48.07 (\pm 0.71)	-31.8 (\pm 1.65)
Si 80-1x	113.19 (\pm 4.80)	116.41 (\pm 10.79)	42.53 (\pm 2.78)	34.93 (\pm 1.46)
Ag/Si 70/10-½x	115.08 (\pm 1.5)	114.38 (\pm 0.14)	-22 (\pm 1.5)	-15.75 (\pm 1.34)
Ag/Si 70/10-1x	159.95 (\pm 2.15)	1083.38 (\pm 155.83)	8.49 (\pm 1.17)	2.91 (\pm 0.80)
Ag/Si 70/10-2x	328.13 (\pm 15.91)	413.07 (\pm 149.58)	11.57 (\pm 0.12)	3.935 (\pm 1.22)
Ag/Si 70/10-½x_SEF	243.33 (\pm 5.35)	273.2 (\pm 4.87)	-16.47 (\pm 0.67)	-11.7 (\pm 1.4)
Ag/Si 70/10-1x_SEF	300.2 (\pm 5.48)	659 (\pm 73)	12.27 (\pm 1.45)	3.73 (\pm 0.78)
Ag/Si 70/10-2x_SEF	507.2 (\pm 13.17)	1008.87 (\pm 86.69)	12.53 (\pm 1.55)	5.74 (\pm 0.62)
Ag/Si 20/7nm-1x	959 (\pm 72.69)	1576.8 (\pm 95.88)	10.03 (\pm 1.03)	7.61 (\pm 0.95)

B Average PDIs for the NPs in different media

Nanoparticle	PDI-MQ	PDI-FW
Ag/Si 70/20-0x	0.101	0.083
Ag/Si 70/20-1x	0.149	0.237
Si 80-0x	0.072	0.120
Si 80-1x	0.140	0.163
Ag/Si 70/10-½x	0.089	0.116
Ag/Si 70/10-1x	0.184	0.571
Ag/Si 70/10-2x	0.361	0.556
Ag/Si 70/10-½x_SEF	0.304	0.314
Ag/Si 70/10-1x_SEF	0.325	0.317
Ag/Si 70/10-2x_SEF	0.345	0.436
Ag/Si 20/7nm-1x	0.483	0.490

C NP tracking analysis measurements in MiliQ water

Nanoparticle	Mean	Mode	StDev	10/50/90*
Ag/Si 70/20-0x	115	88	53	58/103/187
Ag/Si 70/20-1x	124	68	76	51/102/227
Si 80-0x	153	85	82	71/138/245
Si 80-1x	144	100	61	76/131/224
Ag/Si 70/10-½x	84	40	55	31/67/152
Ag/Si 70/10-1x	233	325	115	61/257/358
Ag/Si 70/10-2x	281	103	216	101/199/631
Ag/Si 70/10-½x_SEF	135	100	66	71/120/211
Ag/Si 70/10-1x_SEF	300	314	120	149/289/466
Ag/Si 70/10-2x_SEF	429	342	187	231/386/725
Ag/Si 20/7nm-1x	130	15	124	15/74/332

*size at specific percentiles