

# Service Life of Treated and Untreated Fence Posts

1954 Progress Report on the T. J. Starker Post Farm

(Project No. 29)

By

Robert D. Graham



OREGON FOREST PRODUCTS LABORATORY

State Board of Forestry and School of Forestry,  
Oregon State College, Cooperating  
Corvallis

THE OREGON FOREST PRODUCTS LABORATORY was established by legislative action in 1941 as a result of active interest of the lumber industry and forestry-minded citizens. It is associated with the State Board of Forestry and the School of Forestry at Oregon State College.

An Advisory Committee composed of men from representative interests guides the research program that is directly pointed toward the fuller utilization of Oregon's forest resources. The following men constitute the present membership of the Advisory Committee:

|                                      |  |
|--------------------------------------|--|
| PAUL PATTERSON, Governor . . . .     | <i>Chairman</i>  |
| ROBERT W. COWLIN . . . .             | <i>Pacific Northwest Forest and<br/>Range Experiment Station</i> |
| NILS HULT . . . .                    | <i>Willamette Valley Lumbermen's<br/>Association</i>             |
| CHARLES W. FOX . . . .               | <i>Oregon Plywood Interests</i>                                  |
| WILLIAM SWINDELLS . . . .            | <i>West Coast Lumbermen's<br/>Association</i>                    |
| PAUL M. DUNN . . . .                 | <i>School of Forestry</i>  |
| CARL A. RASMUSSEN . . . .            | <i>Western Pine Association</i>                                  |
| GEORGE SPAUR, State Forester . . . . | <i>Secretary</i>   |

Progress Report 8

October 1954

# Service Life of Treated and Untreated Fence Posts

**1954 Progress Report on the T. J. Starker Post Farm**

**(Project No. 29)**

By

**Robert D. Graham**

In charge, Wood Preservation  
Oregon Forest Products Laboratory

A Research Project of the Oregon Forest Products Laboratory  
Corvallis, Oregon

# Table of Contents

|   | Page |
|---|------|
| Summary of 1954 Inspection .....                                    | 3    |
| The T. J. Starker Post Farm .....                                   | 4    |
| Climatic conditions .....   | 4    |
| Wood-destroying organisms .....                                     | 4    |
| Test specimens .....  | 5    |
| Post inspections .....  | 5    |
| Post farm records .....   | 5    |
| Interpretation of Data .....  | 6    |
| Limitations of test data .....                                      | 6    |
| Influence of climatic conditions .....                              | 6    |
| Consideration of post characteristics .....                         | 7    |
| Equal importance of preservatives and methods of preservation ..... | 7    |
| Preliminary Evaluation of Tests .....                               | 8    |
| Untreated fence posts .....   | 8    |
| Treated fence posts: nonpressure processes .....                    | 9    |
| Treated fence posts: pressure processes .....                       | 10   |
| Method of Applying Preservatives to Test Posts .....                | 11   |
| Preservative Materials Used for Test Posts .....                    | 12   |
| T. J. Starker Post Farm Cooperators .....                           | 28   |

## TABLES

|   |    |
|---|----|
| Table 1. Climatological Data, Corvallis, Oregon .....                           | 15 |
| Table 2. Characteristics of Untreated Fence Posts .....                         | 16 |
| Table 3. Service Records of Untreated Fence Posts .....                         | 17 |
| Table 4. Characteristics of Treated Fence Posts, Nonpressure<br>Processes ..... | 18 |
| Table 5. Service Records of Treated Fence Posts, Nonpressure<br>Processes ..... | 21 |
| Table 6. Characteristics of Treated Fence Posts, Pressure<br>Processes .....    | 23 |
| Table 7. Service Records of Treated Fence Posts, Pressure<br>Processes .....    | 24 |
| Table 8. Removal Records of Untreated Fence Posts .....                         | 25 |
| Table 9. Removal Records of Treated Fence Posts, Nonpressure<br>Processes ..... | 26 |
| Table 10. Removal Records of Treated Fence Posts, Pressure<br>Processes .....   | 27 |

# Service Life of Treated and Untreated Fence Posts

## 1954 Progress Report on the T. J. Starker Post Farm (Project No. 29)

### Summary of 1954 Inspection

Sixty posts from 14 untreated series, 71 posts from 17 non-pressure-treated series, and 5 posts from 2 pressure-treated series failed. Virtually all of the failures of untreated and full-length treated posts occurred at or below the ground, whereas butt-treated posts of nondurable species frequently failed above the ground.

The causes of post failures since 1949 were:

| Cause                         | Number of failures |           |
|-------------------------------|--------------------|-----------|
|                               | 1954               | 1949-1953 |
| Fungi (decay) .....           | 112                | 145       |
| Termites (damp-wood) .....    | 0                  | 13        |
| Fungi and termites .....      | 17                 | 55        |
| Fungi and other insects ..... | 7                  | 15        |

Untreated alder (106)\*, Douglas fir (72, 97, 100), lodgepole pine (103), tanoak (76), and Arizona cypress (84) posts are deteriorating rapidly.

The remaining posts in nonpressure-treated series 6 (Douglas fir) and 9 (Port Orford cedar) failed. Although both series had a service life of about 21 years, the hot-cold bath treatment with carbolinium B was not effective in increasing the service life of Port Orford cedar; the butt treatment of Douglas fir posts with treater dust greatly increased their serviceability. Posts in the following nonpressure-treated series are deteriorating rapidly:

| Species           | Series | Treatment                          |
|-------------------|--------|------------------------------------|
| Cottonwood .....  | 77     | soaking, copper naphthenate        |
| Cottonwood .....  | 78     | Osmoplastic bandage                |
| Douglas fir ..... | 67     | soaking, copper naphthenate        |
| Douglas fir ..... | 73     | Osmoplastic bandage                |
| Douglas fir ..... | 80     | brush, copper naphthenate          |
| Douglas fir ..... | 81     | brush, coal-tar creosote           |
| Douglas fir ..... | 89     | 3 holes, sodium trichlorophenate   |
| Douglas fir ..... | 90     | 3 holes, sodium pentachlorophenate |
| Douglas fir ..... | 91     | 1 hole, salt and mercuric chloride |
| Douglas fir ..... | 92     | brush, Avenarius carbolineum       |

\* Figures refer to series number



The first Chemonite pressure-treated Douglas fir post (45) failed after 17 years of service. The remaining posts in this series are in excellent condition. Failures continued in Douglas fir posts (33) pressure treated with zinc-meta-arsenite; the average service life of posts in this series will approach 25 years.

## **The T. J. Starker Post Farm**

In 1927 the School of Forestry at Oregon State College established and has since maintained a "post farm" to obtain data on the natural durability of native woods and the effectiveness of different preservative treatments for species used as fence-post material. The first posts were set on January 7, 1928, and since the inception of the program, 2,637 posts have been placed in the farm. Three introduced and 24 native species in the untreated condition, and 8 Oregon woods that were given various preservative treatments have been or are being tested.

The T. J. Starker Post Farm is located on School of Forestry land in the Peavy Aboretum about seven miles north of Corvallis, Oregon, on the west side of Highway 99W. The soil in the test area, located on an excellently drained south slope, is Olympic silty-clay loam. The slightly acid top 8 inches of the soil has a pH of 5.4, an organic matter content of 4.71 per cent, a humus of one-half inch or less in thickness, and a nitrogen content of 0.1415 per cent. A number of old Douglas fir stumps are present in the test site.

### **Climatic conditions**

The average annual rainfall in the Corvallis area since 1927 has been about 35 inches with about 130 rainy days per year. Some summer intervals have approached drought conditions. An annual mean relative humidity of 64 per cent and temperature of 53° F. have prevailed. The temperature occasionally falls below freezing and occasionally exceeds 85° F. Cool afternoon breezes from the Pacific Ocean usually arise daily during the summer months. Table 1 gives climatological data for the Corvallis area for the years since 1928.

### **Wood-destroying organisms**

Since 1949, an attempt has been made to determine the various organisms responsible for the deterioration of posts installed in the test site. Although decay-producing fungi are the primary cause of post failures, damp-wood termites, carpenter ants, and wood-boring beetles very frequently contribute to the general deterioration of the posts.

The damp-wood termites swarm during the late summer and early fall. At the time of the annual inspection in early October, discarded wings of the reproductives have been found at the bases of many posts. Entry holes have been made at or below groundline. In only a few instances have termites been the primary cause of failure.

Although carpenter ants have been found in many failed posts, there is evidence to indicate galleries were constructed initially by termites. After destroying the termites, ants usually enlarge the galleries to some extent.

A high proportion of the failed posts have been attacked by wood-boring beetles, although damage seldom approaches that caused by fungi or termites.

### Test specimens

Test posts are usually installed in groups of 25; each group constitutes a test series. Posts in each series are placed 2 feet apart in a row running in a northerly direction up the test plot slope. Test series are spaced 3 feet apart, and all posts are set into the ground to a depth of 2 feet.

Prior to 1947, installed test posts ranged from 4 to 7 feet in length and from 3 to 70 square inches in ground-line cross sectional area. Test posts are now standardized at a length of 5 feet, and cross sectional areas of individual posts are limited to  $16 \pm 8$  square inches at a distance of 2 feet from the butt ends. The average cross sectional area, 2 feet from the butt ends of the posts in each series, must fall within the limits of  $16 \pm 2$  square inches.

### Post inspections

Annual inspections are made during the month of October. A moderate push is applied to the top of each post and each post that breaks is examined to establish the point and cause of failure. Formerly, a 50-pound horizontal pull was applied 2 feet above the ground. A deterioration rating is made of the top by visual inspection, while both the feel of the post and a prod are used to estimate deterioration below the ground.

### Post farm records

Recorded data for each series of posts include the source and species, sizes and types of individual posts, percentage of sapwood, processing prior to installation or preservative treatment, the preservative treatment given (if any), date of installation, dates of individual post failures, the condition of each post at each annual inspection period, and other pertinent facts.

## Interpretation of Data

Posts and other wood products used in contact with the ground and exposed to the weather are subject to attack by insects and wood-destroying fungi. The most vulnerable section of a fence post extends from a short distance above to some distance below the ground surface. This post zone usually has a more sustained favorable supply of the moisture and air necessary to the existence of these destructive agents. In areas of abundant rainfall or prolonged periods of high humidity, the tops of fence posts also are subject to deterioration, but normally it proceeds at a slower rate. The ground-line section of a post also is important because preservatives are most subject to leaching action there and, on windy sites, sand erosion often cuts deeply into the wood of this zone. To evaluate intelligently the results of any test of fence post serviceability, these and many other factors must be considered simultaneously.

### Limitations of test data

The detailed tabular data presented at the end of this report cannot be applied indiscriminately to every locality and to all fence post service requirements. The data are basically comparative and applicable to one area and one type of use; these data must be adjusted empirically to fit other situations.

Posts tested in the T. J. Starker Post Farm are not subject to the stapling, nailing, ground-line erosion, and physical forces that frequently reduce the service life of posts actually in use; but, on the other hand, these test posts are placed in climatic conditions that are conducive to virtually continuous insect attack and decay. The arbitrary method used to determine post failure is admittedly not comparable to the physical forces that may be exerted on fence posts in actual service.

### Influence of climatic conditions

Climate determines to a great extent the proportion of time that suitable conditions for decay exist in a given region. Optimum temperatures for the growth of decay-producing fungi range from 60° to 80° F., but some fungi can develop at temperatures as low as 35° F. or as high as 120° F. If all parts of a wood post have a moisture content of 20 per cent or less (oven-dry basis), there is virtually no possibility of fungus growth. During long periods of extremely dry weather, and in periods when the temperature approaches freezing, the rate of decay in posts is retarded. The rate of post deterioration is doubtlesly much slower in regions where long periods of unfavorable conditions prevail. In western Oregon, for



example, where favorable moisture and temperature conditions exist for long periods, untreated tops of posts that have been given adequate butt treatment with a good preservative often decay long before the ground-line sections are seriously weakened.

### **Consideration of post characteristics**

Post service records in this report mean little, if the characteristics of the wood are not taken into consideration. The size, amount of sapwood, and extractive constituents in the wood greatly influence the serviceability of untreated posts. Larger posts may give longer service, not only because of greater gross volume of wood, but also because of the higher proportion of heartwood that they usually contain. The sapwood of no native species is naturally insect- and decay-resistant. Extractive constituents in the heartwoods of a few species promote resistance to insect and fungus attack; with some exceptions, these extractives give heartwood a darker color than that of sapwood.

### **Equal importance of preservatives and methods of preservation**

The service life of treated wood is affected by the nature of the preservative used, the portion of the product treated, the amount of preservative retained by the wood, the method of treatment, and the uniformity of treatment. Most preservatives are effective fungicides and insecticides, but extension of the service life of wood requires the continued presence of the preservative in a concentration that is toxic to the organisms responsible for deterioration. It is important that the preservative be present in the areas subject to attack, principally the ground-line zone and, in some instances, also the top of the post.

The method of treatment and the preservative used are equally important, for poor treatment produces poor results. For this reason, a preservative cannot be condemned until it can be shown that the treatment was unsatisfactory despite application of the preservative by a proper treating method. Although a preservative may fail under one set of climatic conditions, it may prove extremely successful under different conditions. A preservative that is quite soluble in water, for example, may leach from wood in a region of abundant rainfall, whereas in a dry climate it may be permanent. Successful treatment provides uniform penetration into the treated area and the retention of a sufficient quantity of preservative within the wood structure adequately to protect the wood under the conditions in which it is to be used. High total retention of preservatives is not necessarily an indication of successful treatment; in some species, the end penetration of the preservative may be rapid, whereas side penetration may be slow. This may result in complete protection of the end of the post, with virtually no protection of the ground-line zone.

## Preliminary Evaluation of Tests

Determination of the service life of a series in which most or all posts have failed is relatively simple; for many of the naturally decay-resistant untreated series and for treated series in which few posts have failed, estimation of average service life cannot be made with accuracy. The estimated service life, when given for any series in this report, is based on the number of posts that have failed and on the service age and condition of the remaining posts. For a few untreated species, the natural decay resistance as determined in other service tests has been taken into consideration in making estimates of service life.

### Untreated fence posts

The characteristics, service records, and removal records of untreated fence posts are shown in Tables 2, 3, and 8. Based on the actual and estimated service life for each untreated series of posts, the various species tested or being tested are classified into three broad groups. Numerals in parentheses indicate series numbers for convenience in referring to tabular data.

#### *1. Average service life of at least 20 years*

- Cedar, Alaska yellow (46)
- Cedar, Port Orford (21)
- Cedar, western red (10, 11)
- Juniper, western (30)
- Locust, black (40)
- Osage-orange (32)
- Redwood (58)
- Yew, Pacific (13)

#### *2. Average service life of 10 to 15 years*

- Cedar, incense (29)
- Oak, Oregon white (19)

#### *3. Average service life of less than 10 years*

- Alder, red (16)
- Ash, Oregon (28)
- Cascara (20, 47)
- Cottonwood, black (14, 82)
- Cypress, Arizona (84)
- Douglas fir (1, 55, 57, 72)
- Fir, grand (15)
- Hemlock, West Coast (38)
- Larch, western (37)

Madrone, Pacific (26)  
Maple, Oregon (17)  
Pine, lodgepole (48, 49)  
Pine, ponderosa (36)  
Pine, sugar (35)  
Pine, Idaho white (34)  
Spruce, Sitka (31)  
Tanoak (76)

Initial failures of untreated posts of species showing an average service life of less than 10 years usually occurred at the end of the first 2 or 3 years of service. If such posts must be used, one should expect to replace a few posts after this relatively short time interval, although the average service life of the entire lot may be several times greater than this.

### **Treated fence posts: nonpressure processes**

The characteristics, service records, and removal records for fence posts treated by nonpressure preservation processes are given in Tables 4, 5, and 9. An attempt has been made to evaluate each treatment and, where a treatment has failed to produce a longer average service life than that of untreated material of the same species, the suspected cause of such failure is indicated. Nonpressure preservative treatments have been segregated into two groups on the basis of performance. The names and series numbers of the species receiving these treatments are indicated in parentheses.

#### ***1. Treatments that have not increased the average service life of posts***

BRUSH APPLICATION OF ASPHALT EMULSION (Douglas fir, 39). Brush application of the most efficient preservative can hardly be considered an effective treatment for fence posts. The preservative cannot penetrate the wood sufficiently, and posts retain very little of the preservative.

CHARRING (Douglas fir, 22). Charring is not a preservative treatment and, if it accomplishes anything, it tends to shorten the average service life of posts by producing seasoning checks that give spores of decay-producing fungi access to interior parts of the post and by reducing the volume of wood in the critical zone.

COLD SOAKING IN 5 PER CENT SOLUTION OF ZINC CHLORIDE (Douglas fir, 12). These posts were not appreciably benefited by this treatment for two possible

reasons: (a) inadequate treatment of the ground-line section and (b) leaching of the water-soluble preservative.

HOT AND COLD BATH IN CARBOLINEUM "B" (Port Orford cedar, 9). This treatment seems to have had little effect in increasing the average service life of this species; the service record of untreated Port Orford cedar is very similar to that of the treated material.

OSMOPLASTIC (cottonwood, 78). There was virtually no increase in the service life of posts by this treatment.

**2. *Treatments that have increased the average service life of posts.***

A. C. M. Co. treater dust and paste (Douglas fir, 5, 6, 24, 25).

Hot and cold bath using Carbolineum "B" (Douglas fir, 8).

Hot and cold bath using creosote, black cottonwood, 27).

Hot and cold bath using 50 per cent creosote and 50 per cent crankcase oil (Douglas fir, 18).

Hot and cold bath using Gasco creosote oil (Douglas fir, 54).

Salt treatment (Douglas fir, 2, 3, 4; and lodgepole pine, 50).

Soaking in Permatol "A" (ponderosa pine, 56).

Tire-tube method using Chemonite (Douglas fir, 59).

Reference to the service records (Table 5) of posts in the latter of the two foregoing groups will reveal that many of these nonpressure treatments have been highly effective in protecting the ground-line zone. Serious deterioration in the tops of such posts indicates that some form of top treatment also should be given.

**Treated fence posts: pressure processes**

The characteristics, service records, and removal records of fence posts treated by pressure processes are shown in Tables 6, 7, and 10. The service records of some pressure-treated series are comparatively short, but there is every reason to expect long service life from posts pressure-treated with the preservatives listed below. The names and series numbers of species treated with these preservatives are indicated in parentheses.

1. Chemonite (Douglas fir, 45; and West Coast hemlock, 44).

2. Coal-tar creosote (Douglas fir, 53).

3. Coal-tar creosote and petroleum mixture (Douglas fir, 51).

4. Creosote (Douglas fir, 23).

5. Creosote, 70 per cent and fuel oil, 30 per cent (Douglas fir, 7).
6. Gasco creosote oil (Douglas fir, 52).
7. Wolman (Tanalith) salts (Douglas fir, 42; and West Coast hemlock, 41).
8. Zinc-meta-arsenite (Douglas fir, 33).

Although the service life of Douglas fir (Series 43) has been increased by chromated zinc chloride treatment, eight post failures have occurred in the series, indicating that this preservative treatment has been less effective than those in the foregoing list.

## Methods of Applying Preservatives to Test Posts

**BRUSH TREATMENT:** Preservatives and preservative solutions are applied to the wood surface with a brush. Brush treatment of fence posts cannot be recommended as an effective treatment.

**CHARRING:** Although sometimes called a preservative treatment, charring the surface of wood cannot be justly designated a preservative treatment.

**DOUBLE DIFFUSION:** Green, peeled, or partially peeled posts are placed in a water solution of one chemical for 2 or 3 days and then transferred to a second water solution of a different chemical for 2 or 3 days. The chemicals diffuse into the wood where they react to form a toxic compound that is relatively insoluble in water. The removal of three or more full-length strips of bark improves the distribution of the chemical. Butt-treated posts should be stacked with the tops down to facilitate movement of the chemicals to the tops.

**HOT AND COLD BATH:** In this treatment, often called the open-tank method, the posts are first soaked in a hot preservative solution for a number of hours; then the posts either are allowed to cool in the preservative or are transferred into a cool solution. Posts to be treated by this method should be peeled and thoroughly seasoned. One end, both ends, or the entire length of the post may be treated by this method.

**OSMOPLASTIC BANDAGE:** A 9-inch strip of the bark of a green post is removed at the ground line, and the peeled area is coated with a preservative mixture. A water-resistant covering is tightly wrapped around the coated area. The preservative mixture is also applied to the ends of the post.

**OSMOSALTS:** Osmosalts in a thick water solution are applied to the ends and to the peeled surfaces of green posts, which are then



piled closely and covered for varying periods of time to allow the preservative mixture to diffuse into the wood.

**PRESSURE TREATMENTS:** Prior to treatment, posts are air seasoned, artificially seasoned in the preservative by boiling under vacuum, or conditioned by steaming. Hot preservative is injected into the wood under pressure in a closed container, and a final vacuum is usually applied to remove excess preservative and dry the surface of the wood. The full length of the post receives treatment.

**SALT TREATMENT:** A  $\frac{3}{4}$ -inch hole slanting toward the butt is drilled to a depth of about 2 inches just above the ground line of an unpeeled, freshly cut pole. One tablespoonful of a dry mixture of equal proportions by weight of salt (sodium chloride) and corrosive sublimate (mercuric chloride) or one tablespoonful of dry mixture of equal proportions by weight of salt, corrosive sublimate, and arsenous oxide is placed in the hole. A snug-fitting wood plug is then driven into the hole. The holes should be spaced not more than five inches apart around the circumference of each post and staggered vertically to prevent weakening the post seriously. **Corrosive sublimate and arsenous oxide are very poisonous chemicals that must be handled with extreme care.**

**SOAKING TREATMENT:** Posts are placed in the preservative solution to the desired depth and permitted to soak for a number of hours or days. The posts should be peeled and thoroughly seasoned. For many species, that portion of the post 6 inches above and 12 inches below the ground line should be incised to a depth of one-half inch. This treatment has proved to be very successful for some species and much less effective for others. It is primarily a sapwood treatment.

**TIRE-TUBE METHOD:** One end of a portion of an automobile tire inner tube is slipped over the butt end of an unpeeled, freshly cut post that is laid with the butt end higher than the top end on an inclined rack. The open end of the tire tube is elevated, and the tube is filled with preservative. The preservative, after a period of time, diffuses through the sapwood and finally drips out of the lower end of the post.

## Preservative Materials Used for Test Posts

Virtually all preservatives are poisonous. Many may cause irritations when the chemical itself, its solutions, or its vapor contacts the skin. Some are extremely poisonous and corrosive. Care should be exercised in handling all preservatives; exposed portions of the body should be washed frequently.

**All preservatives should be stored in closed, clearly identified containers. The manufacturer's recommendations should be followed implicitly.**

**ASPHALT EMULSION:** An emulsion or suspension of finely dispersed particles of asphalt in water. Asphalt is a black to a dark brown solid or semisolid material composed predominantly of bitumens.

**BOLIDEN SALTS:** This preservative contains arsenic acid, sodium arsenate, sodium bichromate, and zinc sulfate.

**CARBOLINEUM:** Carbolineum, or anthracene oils, are coal-tar distillates of higher specific gravity and higher boiling range than ordinary coal-tar creosote. The exact composition of Carbolineum "B" is not known.

**CHEMONITE:** Chemonite solution consists of copper, arsenic, and ammonium acetate dissolved in ammoniacal solution.

**CHROMATED ZINC CHLORIDE:** The preservative contains about 82 per cent zinc chloride and 18 per cent sodium bichromate in a water solution.

**COPPER NAPHTHENATE:** The oil-soluble copper salt of naphthenic acid. Solutions containing 2 per cent copper by weight have been recommended for optimum performance.

**CREOSOTE, CREOSOTE OIL, OR COAL-TAR CREOSOTE:** A distillate of coal tar produced by a high-temperature carbonization of bituminous coal. It consists principally of liquid and solid aromatic hydrocarbons, contains appreciable quantities of tar acids and tar bases, and has a continuous boiling-point range that begins at about 200° C. and extends to a temperature at least 125° C. higher.

**CREOSOTE MIXTURES:** Creosote may be mixed in varying proportions with petroleum, crankcase oil, or other diluents that act as carriers for the creosote.

**GASCO CREOSOTE:** A distillate of tar residue resulting from the cracking of asphaltic-base petroleum oils in which artificial fuel gas is the main product.

**OSMOSALTS:** A proprietary wood preservative containing sodium fluoride, sodium bichromate, dinitrophenol, and sometimes arsenic. The chemicals are water-soluble.

**PENTACHLOROPHENOL:** An oil-soluble chemical compound formed from phenol and chlorine. Solutions containing 5 per cent pentachlorophenol by weight are recommended for wood in contact with soil.

PERMATOL "A": A preservative containing pentachlorophenol as its toxic constituent. The name, Permatol, has been copyrighted by the Western Pine Association.

SALT AND CORROSIVE SUBLIMATE: A mixture of equal proportions by weight of the two water-soluble chemicals. Corrosive sublimate (mercuric chloride) is the toxic chemical, and the salt serves to hold moisture. **Corrosive sublimate is an extremely poisonous chemical.**

SALT, CORROSIVE SUBLIMATE, AND ARSENOUS OXIDE: A mixture of equal proportions by weight of the three chemicals. The arsenous oxide is an additional water-soluble toxic agent. The addition of this chemical apparently contributes little, if anything, to the effectiveness of the corrosive sublimate. **Corrosive sublimate is an extremely poisonous chemical.**

SODIUM PENTACHLOROPHENATE: The water-soluble sodium salt of pentachlorophenol.

SODIUM TRICHLOROPHENATE: The water-soluble sodium salt of trichlorophenol.

TREATER DUST, GRANULAR TREATER DUST, AND TREATER PASTE: Preservatives formerly produced by the Anaconda Copper Mining Company as byproducts of its copper smelting operation. Arsenic trioxide is the principal toxic constituent of the preservatives that were sold in dust, granular, and paste forms. The paste form was applied directly to the wood; the dust and granular forms were placed around the posts as earth was backfilled in the post-setting operation. The manufacture of these preservatives has been discontinued.

WOLMAN SALTS (TANALITH): A proprietary wood preservative normally containing sodium fluoride, dinitrophenol, sodium chromate, and sodium arsenate. It is injected in water solution.

ZINC CHLORIDE: A chemical applied to wood in a 2 to 5 per cent water solution.

ZINC-META-ARSENITE: A preservative prepared by dissolving zinc oxide and arsenic trioxide in water that has been acidified with acetic acid.

Table 1. CLIMATOLOGICAL DATA, CORVALLIS, OREGON\*

| Year          | Mean<br>temper-<br>ature | Maxi-<br>mum<br>temper-<br>ature | Mini-<br>mum<br>temper-<br>ature | Mean<br>rela-<br>tive<br>humid-<br>ity | Total<br>rainfall | Mini-<br>mum<br>monthly<br>rainfall | Maxi-<br>mum<br>monthly<br>rainfall | Rainy<br>days |
|---------------|--------------------------|----------------------------------|----------------------------------|--|-------------------|-------------------------------------|-------------------------------------|---------------|
|               | °F                       | °F                               | °F                               | Per<br>cent                            | Inches            | Inches                              | Inches                              | Num-<br>ber   |
| 1928 .....    | 53.4                     | 102                              | 20                               | .....                                  | 39.86             | 0.00                                | 9.43                                | 136           |
| 1929 .....    | 52.7                     | 97                               | 16                               | 70.5                                   | 24.45             | Trace                               | 11.44                               | 98            |
| 1930 .....    | 52.7                     | 98                               | 4                                | 69.2                                   | 23.68             | 0.00                                | 5.07                                | 110           |
| 1931 .....    | 54.4                     | 104                              | 24                               | 68.5                                   | 39.13             | 0.00                                | 9.12                                | 131           |
| 1932 .....    | 53.4                     | 99                               | 9                                | 62.6                                   | 36.94             | Trace                               | 8.09                                | 135           |
| 1933 .....    | 52.3                     | 96                               | 11                               | 64.3                                   | 42.59             | 0.00                                | 14.15                               | 145           |
| 1934 .....    | 55.2                     | 99                               | 26                               | 62.5                                   | 35.42             | 0.10                                | 9.71                                | 115           |
| 1935 .....    | 52.6                     | 106                              | 15                               | 63.0                                   | 26.35             | 0.10                                | 4.76                                | 105           |
| 1936 .....    | 54.2                     | 93                               | 19                               | 67.6                                   | 32.11             | Trace                               | 10.82                               | 121           |
| 1937 .....    | 53.6                     | 98                               | 10                               | 66.8                                   | 58.06             | 0.08                                | 11.17                               | 157           |
| 1938 .....    | 54.3                     | 104                              | 21                               | 64.0                                   | 32.04             | Trace                               | 7.42                                | 139           |
| 1939 .....    | 54.9                     | 104                              | 25                               | 65.6                                   | 26.33             | 0.22                                | 8.53                                | 113           |
| 1940 .....    | 55.7                     | 100                              | 20                               | 67.2                                   | 40.36             | Trace                               | 9.80                                | 128           |
| 1941 .....    | 55.0                     | 104                              | 26                               | 64.7                                   | 32.95             | 0.00                                | 7.99                                | 131           |
| 1942 .....    | 53.9                     | 104                              | 17                               | 59.9                                   | 39.20             | Trace                               | 12.69                               | .....         |
| 1943 .....    | 53.1                     | 95                               | 11                               | 58.2                                   | 31.53             | 0.02                                | 5.60                                | 100           |
| 1944 .....    | 53.2                     | 103                              | 21                               | 58.2                                   | 22.99             | Trace                               | 4.63                                | 97            |
| 1945 .....    | 53.4                     | 98                               | 20                               | 64.4                                   | 37.79             | 0.08                                | 10.08                               | 133           |
| 1946 .....    | 52.2                     | 107                              | 20                               | 61.9                                   | 33.42             | 0.01                                | 6.78                                | 145           |
| 1947 .....    | 53.7                     | 95                               | 18                               | 64.0                                   | 33.91             | 0.16                                | 9.05                                | 141           |
| 1948 .....    | 51.5                     | 97                               | 19                               | 63.6                                   | 40.14             | 0.06                                | 7.46                                | 158           |
| 1949 .....    | 52.5                     | 95                               | 12                               | 61.2                                   | 34.84             | Trace                               | 11.84                               | 135           |
| 1950 .....    | 53.0                     | 99                               | —1                               | 68.1                                   | 48.58             | 0.21                                | 12.17                               | 171           |
| 1951 .....    | 53.3                     | 99                               | 18                               | 66.5                                   | 38.38             | 0.02                                | 7.36                                | 136           |
| 1952 .....    | 52.3                     | 100                              | 15                               | .....                                  | 27.68             | 0.00                                | 7.13                                | 118           |
| 1953 .....    | 52.3                     | 94                               | 25                               | .....                                  | 50.21             | Trace                               | 12.23                               | 170           |
| Average ..... | 53.4                     | 100                              | 17                               | 64.5                                   | 35.73             | .....                               | .....                               | 131           |

\* Data from Agricultural Experiment Station, Oregon State College, Corvallis.

Table 2. CHARACTERISTICS OF UNTREATED FENCE POSTS

| Species                   | Series number | Number of posts in test | Post description                  | Sap-wood        | Ground-line perimeter |               |               | Remarks                  |
|---------------------------|---------------|-------------------------|-----------------------------------|-----------------|-----------------------|---------------|---------------|--------------------------|
|                           |               |                         |                                   |                 | Mini-mum              | Maxi-mum      | Aver-age      |                          |
|                           |               |                         |                                   | <i>Per cent</i> | <i>Inches</i>         | <i>Inches</i> | <i>Inches</i> |                          |
| Alder, red .....          | 16            | 25                      | Split                             | 25              | 15.0                  | 24.0          | 19.6          |                          |
| Alder, red .....          | 106           | 25                      | Round, peeled                     | 100             | 9.7                   | 18.5          | 11.9          |                          |
| Ash, Oregon .....         | 28            | 25                      | Split                             | 30              | 14.4                  | 24.0          | 19.2          |                          |
| Cascara .....             | 20            | 12                      | Round, peeled                     | 70              | 6.0                   | 13.3          | 8.9           |                          |
| Cascara .....             | 47            | 26                      | Round, unpeeled                   | 35              | 12.6                  | 30.2          | 17.3          |                          |
| Cedar, Alaska .....       | 46            | 24                      | Split, mostly heartwood           | ....            | 13.0                  | 22.5          | 17.7          | From tree down 4 years   |
| Cedar, incense .....      | 29            | 25                      | Split                             | 0               | 15.6                  | 26.4          | 20.4          |                          |
| Cedar, Port Orford .....  | 21            | 25                      | Split                             | 0               | 17.0                  | 32.0          | 24.4          |                          |
| Cedar, western red .....  | 10*           | 25                      | Split                             | 0               | 18.0                  | 23.0          | 19.9          | Selected for dark color  |
| Cedar, western red .....  | 11*           | 25                      | Split                             | 0               | 17.0                  | 21.0          | 19.1          | Selected for light color |
| Cottonwood, black .....   | 14            | 25                      | Split                             | 20              | 17.0                  | 28.0          | 22.4          |                          |
| Cottonwood, black .....   | 82            | 25                      | Round, unpeeled                   | 95              | 9.7                   | 17.6          | 14.1          |                          |
| Cypress, Arizona .....    | 84            | 25                      | Round, unpeeled                   | 100             | 10.4                  | 14.7          | 12.6          |                          |
| Douglas fir .....         | 1             | 25                      | Round, unpeeled                   | 60              | 15.5                  | 22.0          | 19.1          |                          |
| Douglas fir .....         | 55            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Douglas fir .....         | 57            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Douglas fir .....         | 72            | 25                      | Round, unpeeled                   | 48              | 10.4                  | 16.3          | 13.5          |                          |
| Douglas fir .....         | 97            | 25                      | Square                            | 5               | 14.5                  | 14.5          | 14.5          |                          |
| Douglas fir .....         | 100           | 25                      | Round, 4 strips peeled            | 80              | 12.6                  | 19.8          | 16.3          |                          |
| Fir, grand .....          | 15            | 25                      | Split                             | 65              | 17.5                  | 28.0          | 22.4          |                          |
| Hemlock, West Coast ..... | 38            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Juniper, western .....    | 30            | 11                      | Round, peeled                     | 40              | 19.0                  | 26.5          | 22.1          |                          |
| Juniper, western .....    | 30            | 14                      | Split                             | 40              | 17.5                  | 27.5          | 23.9          |                          |
| Larch, western .....      | 37            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Locust, black .....       | 40            | 8                       | Round                             | 20              | 6.3                   | 17.3          | 10.4          |                          |
| Locust, black .....       | 40            | 14                      | Split                             | 20              | 11.3                  | 27.0          | 15.8          |                          |
| Madrone, Pacific .....    | 26            | 25                      | Round and split                   | 40              | 16.5                  | 27.5          | 21.2          |                          |
| Maple, Oregon .....       | 17            | 25                      | Split                             | 25              | 17.5                  | 24.5          | 20.4          |                          |
| Metal .....               | 60            | 25                      | Angle iron, 1.1 lb. per foot      | ....            | ....                  | ....          | ....          | Aluminum paint           |
| Metal .....               | 61            | 25                      | "T" post, 1.2 lb. per foot        | ....            | ....                  | ....          | ....          | Red oxide paint          |
| Metal .....               | 69            | 9                       | H-beam, 4 lb. per foot            | ....            | ....                  | ....          | ....          | Green enamel, baked      |
| Metal .....               | 70            | 10                      | Flanged channel, 1.3 lb. per foot | ....            | ....                  | ....          | ....          | Green enamel, baked      |
| Metal .....               | 71            | 10                      | "T" post, 1.5 lb. per foot        | ....            | ....                  | ....          | ....          | Green enamel, baked      |
| Oak, Oregon white .....   | 19            | 24                      | Split                             | 20              | 15.0                  | 23.5          | 18.5          |                          |
| Osage-orange .....        | 32            | 11                      | Round, unpeeled                   | 10              | 15.8                  | 26.0          | 20.1          |                          |
| Osage-orange .....        | 32            | 15                      | Split                             | 10              | 12.6                  | 20.6          | 17.5          |                          |
| Pine, lodgepole .....     | 48            | 26                      | Round, peeled                     | 55              | 12.6                  | 18.8          | 15.7          | From dead trees          |
| Pine, lodgepole .....     | 49            | 25                      | Round, peeled                     | 55              | 12.6                  | 18.8          | 15.7          | From live trees          |
| Pine, lodgepole .....     | 103           | 25                      | Round, 4 strips peeled            | 80              | 9.1                   | 16.7          | 11.9          |                          |
| Pine, ponderosa .....     | 36            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Pine, sugar .....         | 35            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Pine, Idaho white .....   | 34            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Redwood .....             | 58            | 25                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Spruce, Sitka .....       | 31            | 26                      | Square                            | 0               | 16.0                  | 16.0          | 16.0          |                          |
| Tanoak .....              | 76            | 25                      | Round, unpeeled                   | 100             | 9.1                   | 15.4          | 12.2          |                          |
| Yew, Pacific .....        | 13            | 23                      | Round, peeled                     | 10              | 9.7                   | 23.2          | 15.7          |                          |

\* From same group of posts.



Table 3. SERVICE RECORDS OF UNTREATED FENCE POSTS

| Species                   | Series number | Number of posts in test | Number of posts removed at last inspection | Number of posts remaining | Average service life of removed posts | Service age of remaining posts | Location and extent of deterioration in remaining posts |                        |                        |                        |
|---------------------------|---------------|-------------------------|--|---------------------------|---------------------------------------|--------------------------------|---|------------------------|------------------------|------------------------|
|                           |               |                         |  |                           |                                       |                                | Ground-line zone  |                        | Top                    |                        |
|                           |               |                         |  |                           |                                       |                                | Little or none  | Moderate to severe     | Little or none         | Moderate to severe     |
|                           |               |                         |  |                           | <i>Years</i>                          | <i>Years</i>                   | <i>Number of posts</i>                                  | <i>Number of posts</i> | <i>Number of posts</i> | <i>Number of posts</i> |
| Alder, red .....          | 16            | 25                      | ....                                       | 0                         | 5.2                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Alder, red .....          | 106           | 25                      | 4  | 21                        | 1.9                                   | 1.9                            | 0   | 21                     | 21                     | 0                      |
| Ash, Oregon .....         | 28            | 25                      | ....                                       | 0                         | 6.2                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Cascara .....             | 20            | 12                      | ....                                       | 0                         | 5.4                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Cascara .....             | 47            | 26                      | ....                                       | 1                         | 7.2                                   | 16.7                           | 0   | 1                      | 0                      | 1                      |
| Cedar, Alaska .....       | 46            | 24                      | 9  | 10                        | 15.9                                  | 16.9                           | 2   | 8                      | 7                      | 3                      |
| Cedar incense .....       | 29            | 25                      | ....                                       | 2                         | 13.3                                  | 24.6                           | 0   | 2                      | 2                      | 0                      |
| Cedar, Port Orford .....  | 21            | 25                      | ....                                       | 0                         | 20.2                                  | ....                           | ....  | ....                   | ....                   | ....                   |
| Cedar, western red .....  | 10            | 25                      | 3  | 6                         | 22.0                                  | 25.6                           | 0   | 6                      | 6                      | 0                      |
| Cedar, western red .....  | 11            | 25                      | 2  | 2                         | 21.3                                  | 25.5                           | 0   | 2                      | 2                      | 0                      |
| Cottonwood, black .....   | 14            | 25                      | ....                                       | 0                         | 4.8                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Cottonwood, black .....   | 82            | 25                      | 5  | 2                         | 4.2                                   | 5.5                            | 0   | 2                      | 2                      | 0                      |
| Cypress, Arizona .....    | 84            | 25                      | 9  | 14                        | 2.8                                   | 3.0                            | 3   | 11                     | 14                     | 0                      |
| Douglas fir .....         | 1             | 25                      | ....                                       | 0                         | 7.0                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....         | 55            | 25                      | ....                                       | 0                         | 6.2                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....         | 57            | 25                      | ....                                       | 0                         | 4.0                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....         | 72            | 25                      | 3  | 13                        | 4.9                                   | 5.8                            | 0   | 13                     | 8                      | 5                      |
| Douglas fir .....         | 97            | 25                      | 1  | 24                        | 1.9                                   | 1.9                            | 19  | 5                      | 24                     | 0                      |
| Douglas fir .....         | 100           | 25                      | ....                                       | 25                        | ....                                  | 1.9                            | 19  | 6                      | 25                     | 0                      |
| Fir, grand .....          | 15            | 25                      | ....                                       | 0                         | 8.7                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Hemlock, West Coast ..... | 38            | 25                      | ....                                       | 0                         | 5.8                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Juniper, western .....    | 30            | 25                      | 4  | 8                         | 21.2                                  | 24.7                           | 0   | 8                      | 5                      | 3                      |
| Larch, western .....      | 37            | 25                      | ....                                       | 0                         | 7.3                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Locust, black .....       | 40            | 22                      | 1  | 13                        | 17.7                                  | 19.5                           | 9   | 4                      | 13                     | 0                      |
| Madrone, Pacific .....    | 26            | 25                      | ....                                       | 0                         | 5.8                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Maple, Oregon .....       | 17            | 25                      | ....                                       | 0                         | 6.5                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Metal, Angle iron .....   | 60            | 25                      | ....                                       | 25                        | ....                                  | 5.9                            | 25  | 0                      | 25                     | 0                      |
| Metal, T-post .....       | 61            | 25                      | ....                                       | 25                        | ....                                  | 5.9                            | 25  | 0                      | 25                     | 0                      |
| Metal, H-beam .....       | 69            | 9                       | ....                                       | 9                         | ....                                  | 5.8                            | 9   | 0                      | 9                      | 0                      |
| Metal, Channel .....      | 70            | 10                      | ....                                       | 10                        | ....                                  | 5.8                            | 10  | 0                      | 10                     | 0                      |
| Metal, T-post .....       | 71            | 10                      | ....                                       | 10                        | ....                                  | 5.8                            | 10  | 0                      | 10                     | 0                      |
| Oak, Oregon white .....   | 19            | 23                      | 2  | 6                         | 13.9                                  | 25.4                           | 1   | 5                      | 1                      | 5                      |
| Osage-orange .....        | 32            | 26                      | ....                                       | 26                        | ....                                  | 21.5                           | 26  | 0                      | 26                     | 0                      |
| Pine, lodgepole .....     | 48            | 26                      | ....                                       | 0                         | 5.1                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Pine, lodgepole .....     | 49            | 25                      | ....                                       | 0                         | 4.0                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Pine, lodgepole .....     | 103           | 25                      | 6  | 19                        | 1.9                                   | 1.9                            | 0   | 19                     | 19                     | 0                      |
| Pine, ponderosa .....     | 36            | 25                      | ....                                       | 0                         | 6.4                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Pine, sugar .....         | 35            | 25                      | ....                                       | 0                         | 7.3                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Pine, Idaho white .....   | 34            | 25                      | ....                                       | 0                         | 5.8                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Redwood .....             | 58            | 25                      | ....                                       | 23                        | 10.8                                  | 14.7                           | 21  | 2                      | 23                     | 0                      |
| Spruce, Sitka .....       | 31            | 26                      | ....                                       | 0                         | 5.7                                   | ....                           | ....  | ....                   | ....                   | ....                   |
| Tanoak .....              | 76            | 25                      | 7  | 18                        | 3.0                                   | 3.0                            | 0   | 18                     | 18                     | 0                      |
| Yew, Pacific .....        | 13            | 23                      | 4  | 12                        | 17.4                                  | 25.6                           | 0   | 12                     | 8                      | 4                      |

Table 4. CHARACTERISTICS OF TREATED FENCE POSTS  
Nonpressure processes

| Species                 | Series number | Post description                 | Sap-wood        | Ground-line perimeter |               |               | Preservative treatment*  | Average retention per cubic foot |               | Average total retention per post |
|-------------------------|---------------|----------------------------------|-----------------|-----------------------|---------------|---------------|--|----------------------------------|---------------|----------------------------------|
|                         |               |                                  |                 | Mini-<br>mum          | Maxi-<br>mum  | Aver-<br>age  |  | Butt                             | Top           |                                  |
|                         |               |                                  | <i>Per cent</i> | <i>Inches</i>         | <i>Inches</i> | <i>Inches</i> |  | <i>Pounds</i>                    | <i>Pounds</i> | <i>Pounds</i>                    |
| Alder, red .....        | 105           | Round, peeled, green             | 100             | 9.7                   | 18.5          | 11.9          | Double diffusion, butts, 6 per cent copper sulfate—2 days; 8 per cent sodium chromate—2 days | .....                            | .....         | .....                            |
| Alder, red .....        | 108           | Round, green, 4 strips peeled    | 100             | 9.4                   | 17.3          | 13.2          | Double diffusion, butts, 4 per cent sodium fluoride—2 days; 6 per cent copper sulfate—2 days | .....                            | .....         | .....                            |
| Cedar, Port Orford .... | 9             | Round, peeled                    | 25              | 18.0                  | 21.5          | 19.5          | Hot-cold bath, carbolineum "B," butt   | .....                            | .....         | .....                            |
| Cottonwood, black ....  | 27            | Split, peeled                    | 20              | 16.5                  | 24.5          | 21.6          | Hot-cold bath, creosote, B-6   | .....                            | .....         | .....                            |
| Cottonwood, black ....  | 68            | Round, peeled, incised           | 89              | 11.0                  | 17.3          | 13.5          | Soak, 5 per cent pentachlorophenol-diesel oil, B-6, T-1                                      | 7.31                             | 4.06          | 2.86                             |
| Cottonwood, black ....  | 74            | Round, peeled, incised           | 99              | 11.0                  | 16.0          | 13.5          | Soak, 5 per cent sodium pentachlorophenate, B-4, T-1   | 7.66                             | 4.47          | 2.93                             |
| Cottonwood, black ....  | 77            | Round, peeled, incised           | 95              | 11.0                  | 17.3          | 13.5          | Soak, copper naphthenate-diesel oil (1 per cent copper), B-6, T-1                            | 2.71                             | 1.47          | 1.04                             |
| Cottonwood, black ....  | 78            | Round, ground-line peeled, green | 83              | 11.3                  | 16.6          | 13.8          | Osmoplastic bandage  | .....                            | .....         | .....                            |
| Cottonwood, black ....  | 87            | Round, peeled, incised           | 90              | 11.0                  | 17.3          | 14.1          | Soak, Gasco creosote oil, B-3, T-2   | 10.9                             | 10.1          | 5.80                             |
| Douglas fir .....       | 39            | Round, peeled                    | 60              | 15.5                  | 22.0          | 19.1          | Brush, asphalt emulsion, butt  | .....                            | .....         | .....                            |
| Douglas fir .....       | 79            | Round, peeled                    | 40              | 10.4                  | 17.0          | 14.1          | Brush, 2 coats, 5 per cent pentachlorophenol-diesel oil                                      | .....                            | .....         | .....                            |
| Douglas fir .....       | 80            | Round, peeled                    | 46              | 10.4                  | 18.5          | 13.8          | Brush, 2 coats, copper naphthenate-diesel oil  | .....                            | .....         | .....                            |
| Douglas fir .....       | 81            | Round, peeled                    | 44              | 11.3                  | 17.9          | 14.8          | Brush, 2 coats, coal-tar creosote  | .....                            | .....         | .....                            |
| Douglas fir .....       | 92            | Round, peeled                    | 46              | 9.4                   | 18.2          | 14.1          | Brush, 2 coats Avenarius carbolineum   | .....                            | .....         | .....                            |
| Douglas fir .....       | 22            | Round, peeled                    | 60              | 12.5                  | 19.3          | 14.7          | Charred $\frac{1}{4}$ inch deep, butt  | .....                            | .....         | .....                            |
| Douglas fir .....       | 101           | Round, green, 4 strips peeled    | 65              | 12.9                  | 19.2          | 17.0          | Double diffusion, butts, 4 per cent sodium fluoride—2 days; 6 per cent copper sulfate—2 days | .....                            | .....         | .....                            |
| Douglas fir .....       | 102           | Round, green, 4 strips peeled    | 65              | 13.8                  | 18.8          | 16.3          | Double diffusion, butts, 6 per cent copper sulfate—2 days; 8 per cent sodium chromate—2 days | .....                            | .....         | .....                            |

\* B (butt) and T (top) are followed by treating time in hours.

Table 4. CHARACTERISTICS OF TREATED FENCE POSTS (Continued)  
Nonpressure processes

| Species     | Series number | Post description                 | Sap-wood | Ground-line perimeter |         |         | Preservative treatment*  | Average retention per cubic foot |        | Average total retention per post |
|-------------|---------------|----------------------------------|----------|-----------------------|---------|---------|--|----------------------------------|--------|----------------------------------|
|             |               |                                  |          | Minimum               | Maximum | Average |  | Butt                             | Top    |                                  |
|             |               |                                  | Per cent | Inches                | Inches  | Inches  |  | Pounds                           | Pounds | Pounds                           |
| Douglas fir | 2             | Round, unpeeled, green           | 60       | 14.0                  | 22.7    | 18.3    | Salt and mercuric chloride, 1 hole, butt                           | .....                            | .....  | .....                            |
| Douglas fir | 91            | Round, unpeeled, green           | 32       | 10.4                  | 16.6    | 14.1    | Salt and mercuric chloride (2:1), 1 hole, butt                     | .....                            | .....  | .....                            |
| Douglas fir | 3             | Round, unpeeled, green           | 60       | 15.0                  | 26.0    | 19.9    | Salt, mercuric chloride, and arsenous oxide, 2 holes, butt         | .....                            | .....  | .....                            |
| Douglas fir | 4             | Round, unpeeled, green           | 60       | 15.0                  | 22.0    | 17.5    | Salt, mercuric chloride, and arsenous oxide, 3 holes, butt         | .....                            | .....  | .....                            |
| Douglas fir | 89            | Round, unpeeled, green           | 45       | 9.4                   | 17.3    | 14.1    | Sodium trichlorophenate, 3 holes, butt                             | .....                            | .....  | .....                            |
| Douglas fir | 90            | Round, unpeeled, green           | 39       | 11.3                  | 17.3    | 14.1    | Sodium pentachlorophenate, 3 holes, butt                           | .....                            | .....  | .....                            |
| Douglas fir | 5             | Round, unpeeled, green           | 60       | 13.0                  | 20.5    | 15.6    | A.C.M. Co. treater dust, butt                                      | .....                            | .....  | .....                            |
| Douglas fir | 6             | Round, unpeeled, green           | 60       | 13.0                  | 20.5    | 16.5    | A.C.M. Co. granulated treater dust, butt                           | .....                            | .....  | .....                            |
| Douglas fir | 24            | Round, peeled, green             | 60       | 12.0                  | 18.5    | 14.4    | A.C.M. Co. treater paste, butt                                     | .....                            | .....  | 2.00                             |
| Douglas fir | 25            | Round, peeled, green             | 60       | 12.5                  | 18.0    | 15.5    | A.C.M. Co. treater paste, butt                                     | .....                            | .....  | 4.00                             |
| Douglas fir | 59            | Round, unpeeled, green           | 60       | 13.6                  | 21.4    | 17.4    | Tire-tube, full-length diffusion, Chemonite                        | .....                            | .....  | 6.00                             |
| Douglas fir | 73            | Round, ground-line peeled, green | 58       | 11.0                  | 16.6    | 14.1    | Osmoplastic bandage  | .....                            | .....  | .....                            |
| Douglas fir | 75            | Round, peeled, green             | 46       | 11.0                  | 17.3    | 14.1    | Osmosalts, covered 30 days   | .....                            | .....  | .....                            |
| Douglas fir | 12            | Round, peeled                    | 60       | 11.9                  | 16.7    | 13.8    | Soak, 5 per cent zinc chloride, B-192                              | .....                            | .....  | .....                            |
| Douglas fir | 62            | Round, peeled, incised           | 33       | 11.3                  | 16.0    | 13.8    | Soak, 5 per cent pentachlorophenol-diesel oil, B-2, T-2            | 1.02                             | 0.40   | 0.37                             |
| Douglas fir | 63            | Round, peeled, incised           | 26       | 10.4                  | 17.6    | 13.5    | Soak, copper naphthenate-diesel oil (1 per cent copper), B-48, T-6 | 1.64                             | 0.26   | 0.50                             |
| Douglas fir | 64            | Round, peeled, incised           | 46       | 10.4                  | 17.3    | 14.1    | Soak, 5 per cent pentachlorophenol-diesel oil, B-48, T-6           | 2.22                             | 0.45   | 0.95                             |
| Douglas fir | 65            | Round, peeled, incised           | 40       | 11.0                  | 16.3    | 14.1    | Soak, copper naphthenate-diesel oil (1 per cent copper), B-2, T-2  | 0.75                             | 0.30   | 0.29                             |
| Douglas fir | 66            | Round, peeled                    | 40       | 11.0                  | 17.3    | 14.1    | Soak, 5 per cent pentachlorophenol-diesel oil, B-48, T-6           | 1.03                             | 0.23   | 0.35                             |

\* B (butt) and T (top) are followed by treating time in hours.

Table 4. CHARACTERISTICS OF TREATED FENCE POSTS (Continued)  
Nonpressure processes

| Species               | Series number | Post description               | Sap-wood        | Ground-line perimeter |               |               | Preservative treatment*   | Average retention per cubic foot |               | Average total retention per post |
|-----------------------|---------------|--------------------------------|-----------------|-----------------------|---------------|---------------|---|----------------------------------|---------------|----------------------------------|
|                       |               |                                |                 | Minimum               | Maximum       | Average       |   | Butt                             | Top           |                                  |
|                       |               |                                | <i>Per cent</i> | <i>Inches</i>         | <i>Inches</i> | <i>Inches</i> |   | <i>Pounds</i>                    | <i>Pounds</i> | <i>Pounds</i>                    |
| Douglas fir .....     | 67            | Round, peeled                  | 33              | 10.7                  | 17.3          | 13.8          | Soak, copper naphthenate-diesel oil (1 per cent copper), B-48, T-6  | 0.73                             | 0.24          | 0.25                             |
| Douglas fir .....     | 88            | Round, butt peeled and incised | 40              | 9.4                   | 18.5          | 13.8          | Soak, Gasco creosote oil, B-168, T-48   | 3.1                              | 2.2           | 1.40                             |
| Douglas fir .....     | 93            | Round, peeled, incised         | 32              | 9.4                   | 17.0          | 14.1          | Soak, copper naphthenate-diesel oil (1 per cent copper), B-144, T-48  | 3.0                              | 1.2           | 1.20                             |
| Douglas fir .....     | 94            | Round, peeled, incised         | 33              | 11.6                  | 16.3          | 13.8          | Soak, 5 per cent pentachlorophenol-diesel oil, B-144, T-48  | 3.5                              | 1.5           | 1.30                             |
| Douglas fir .....     | 95            | Round, peeled, incised         | 32              | 11.3                  | 17.3          | 14.1          | Soak, Gasco creosote oil, B-144, T-48   | 3.2                              | 1.5           | 1.30                             |
| Douglas fir .....     | 8             | Round, peeled                  | 60              | 10.0                  | 21.2          | 16.6          | Hot-cold bath, butt, Carbolinum "B," B-6  | .....                            | .....         | .....                            |
| Douglas fir .....     | 18            | Round, peeled                  | 60              | 12.0                  | 18.0          | 15.8          | Hot-cold bath, creosote and crankcase oil (50/50), B-20   | .....                            | .....         | 0.88                             |
| Douglas fir .....     | 54            | Square                         | 0               | 16.0                  | 16.0          | 16.0          | Hot-cold bath, Gasco creosote, B-6  | .....                            | .....         | 0.57                             |
| Maple, Oregon .....   | 83            | Round, peeled, incised         | 75              | 11.0                  | 17.3          | 14.1          | Soak, 5 per cent pentachlorophenol-diesel oil, B-24, T-2  | 7.49                             | 2.03          | 2.72                             |
| Pine, lodgepole ..... | 99            | Round, green, 4 strips peeled  | 75              | 9.1                   | 15.4          | 12.3          | Double diffusion, butts, 6 per cent copper sulfate—2 days; 8 per cent sodium chromate—2 days                              | .....                            | .....         | .....                            |
| Pine, lodgepole ..... | 104           | Round, green, 4 strips peeled  | 80              | 9.4                   | 18.2          | 13.5          | Double diffusion, butts, 5 per cent zinc sulfate plus 0.7 per cent arsenic acid—2 days; 8 per cent sodium chromate—2 days | .....                            | .....         | .....                            |
| Pine, lodgepole ..... | 50            | Round, unpeeled                | 55              | 12.6                  | 19.8          | 15.5          | Salt, mercuric chloride, and arsenous oxide, 1 hole, butt   | .....                            | .....         | .....                            |
| Pine, lodgepole ..... | 85            | Round, peeled, incised         | 65              | 11.9                  | 16.0          | 13.5          | Soak, Gasco creosote oil, B-43, T-24  | 4.1                              | 1.8           | 1.5                              |
| Pine, lodgepole ..... | 86            | Round, peeled, incised         | 76              | 9.7                   | 16.3          | 13.5          | Soak, 5 per cent pentachlorophenol-diesel oil, B-43, T-24   | 4.1                              | 2.5           | 1.6                              |
| Pine, ponderosa ..... | 56            | Square                         | 0-35            | 16.0                  | 16.0          | 16.0          | Soak, Permatol "A," 17 hours  | .....                            | .....         | 0.61                             |

\*B (butt) and T (top) are followed by treating time in hours.

Table 5. SERVICE RECORDS OF TREATED FENCE POSTS  
Nonpressure processes

| Species                  | Series number | Number of posts in test | Number of posts removed at last inspection | Number of posts remaining | Average service life of removed posts | Service age of remaining posts | Location and extent of deterioration in remaining posts |                        |                        |                        |
|--------------------------|---------------|-------------------------|--|---------------------------|---------------------------------------|--------------------------------|---|------------------------|------------------------|------------------------|
|                          |               |                         |  |                           |                                       |                                | Ground-line zone  |                        | Top                    |                        |
|                          |               |                         |  |                           |                                       |                                | Little or none  | Moderate to severe     | Little or none         | Moderate to severe     |
|                          |               |                         |  |                           | <i>Years</i>                          | <i>Years</i>                   | <i>Number of posts</i>                                  | <i>Number of posts</i> | <i>Number of posts</i> | <i>Number of posts</i> |
| Alder, red .....         | 105           | 25                      | ....                                       | 25                        | .....                                 | 1.9                            | 25  | 0                      | 25                     | 0                      |
| Alder, red .....         | 108           | 25                      | ....                                       | 25                        | .....                                 | 1.9                            | 25  | 0                      | 25                     | 0                      |
| Cedar, Port Orford ..... | 9             | 10                      | 1  | 0                         | 21.1                                  | .....                          | ....  | ....                   | ....                   | ....                   |
| Cottonwood, black* ..... | 27            | 24                      | ....                                       | 0                         | 22.2                                  | .....                          | ....  | ....                   | ....                   | ....                   |
| Cottonwood, black .....  | 68            | 25                      | ....                                       | 25                        | .....                                 | 5.8                            | 25  | 0                      | 25                     | 0                      |
| Cottonwood, black .....  | 74            | 22                      | 1  | 21                        | 5.5                                   | 5.5                            | 16  | 5                      | 20                     | 1                      |
| Cottonwood, black .....  | 77            | 25                      | 3  | 12                        | 4.4                                   | 5.5                            | 0   | 12                     | 12                     | 0                      |
| Cottonwood, black .....  | 78            | 25                      | 12   | 1                         | 4.9                                   | 5.6                            | 0   | 1                      | 1                      | 0                      |
| Cottonwood, black .....  | 87            | 25                      | ....                                       | 25                        | .....                                 | 3.9                            | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....        | 39            | 25                      | ....                                       | 0                         | 5.3                                   | .....                          | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....        | 79            | 25                      | ....                                       | 25                        | .....                                 | 4.9                            | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....        | 80            | 25                      | ....                                       | 25                        | .....                                 | 5.0                            | 17  | 8                      | 25                     | 0                      |
| Douglas fir .....        | 81            | 23                      | 5  | 17                        | 5.7                                   | 5.9                            | 5   | 12                     | 17                     | 0                      |
| Douglas fir .....        | 92            | 25                      | 11   | 14                        | 4.9                                   | 4.9                            | 0   | 14                     | 14                     | 0                      |
| Douglas fir .....        | 22            | 25                      | ....                                       | 0                         | 6.3                                   | .....                          | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....        | 101           | 25                      | ....                                       | 25                        | .....                                 | 1.9                            | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....        | 102           | 25                      | ....                                       | 25                        | .....                                 | 1.9                            | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....        | 2             | 23                      | 1  | 22                        | 26.7                                  | 26.7                           | 0   | 22                     | 0                      | 22                     |
| Douglas fir .....        | 91            | 25                      | ....                                       | 25                        | .....                                 | 4.9                            | 0   | 25                     | 25                     | 0                      |
| Douglas fir .....        | 3             | 22                      | ....                                       | 22                        | .....                                 | 26.7                           | 0   | 22                     | 1                      | 21                     |
| Douglas fir .....        | 4             | 22                      | ....                                       | 22                        | .....                                 | 26.7                           | 3   | 19                     | 6                      | 16                     |
| Douglas fir .....        | 89            | 25                      | 4  | 18                        | 4.6                                   | 5.5                            | 0   | 18                     | 18                     | 0                      |
| Douglas fir .....        | 90            | 25                      | 6  | 11                        | 4.7                                   | 5.5                            | 0   | 11                     | 11                     | 0                      |
| Douglas fir .....        | 5             | 25                      | 4  | 18                        | 25.1                                  | 26.6                           | 1   | 17                     | 12                     | 6                      |
| Douglas fir .....        | 6             | 25                      | 6  | 0                         | 20.9                                  | .....                          | ....  | ....                   | ....                   | ....                   |
| Douglas fir .....        | 24            | 25                      | 2  | 20                        | 21.7                                  | 24.7                           | 9   | 11                     | 14                     | 6                      |

\* The average service life of butts of these posts would have been greater than 22 years, whereas the average service life of the tops probably was less than 10 years.



Table 5. SERVICE RECORDS OF TREATED FENCE POSTS (Continued)  
Nonpressure processes

| Species               | Series number | Number of posts in test | Number of posts removed at last inspection | Number of posts remaining | Average service life of removed posts | Service age of remaining posts | Location and extent of deterioration in remaining posts |                    |                 |                    |
|-----------------------|---------------|-------------------------|--|---------------------------|---------------------------------------|--------------------------------|---|--------------------|-----------------|--------------------|
|                       |               |                         |  |                           |                                       |                                | Ground-line zone  |                    | Top             |                    |
|                       |               |                         |  |                           |                                       |                                | Little or none  | Moderate to severe | Little or none  | Moderate to severe |
|                       |               |                         |  |                           | Years                                 | Years                          | Number of posts   | Number of posts    | Number of posts | Number of posts    |
| Douglas fir .....     | 25            | 25                      | 2  | 19                        | 21.0                                  | 24.7                           | 5   | 14                 | 9               | 10                 |
| Douglas fir .....     | 59            | 12                      | .....                                      | 12                        | .....                                 | 12.3                           | 12  | 0                  | 7               | 5                  |
| Douglas fir .....     | 73            | 25                      | 2  | 22                        | 5.5                                   | 5.8                            | 14  | 8                  | 22              | 0                  |
| Douglas fir .....     | 75            | 25                      | .....                                      | 25                        | .....                                 | 5.5                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 12            | 25                      | .....                                      | 0                         | 7.0                                   | .....                          | .....   | .....              | .....           | .....              |
| Douglas fir .....     | 62            | 25                      | .....                                      | 25                        | .....                                 | 5.7                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 63            | 25                      | .....                                      | 25                        | .....                                 | 5.7                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 64            | 25                      | .....                                      | 25                        | .....                                 | 5.8                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 65            | 25                      | 3  | 21                        | 5.0                                   | 5.5                            | 21  | 0                  | 21              | 0                  |
| Douglas fir .....     | 66            | 25                      | .....                                      | 25                        | .....                                 | 5.5                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 67            | 25                      | 3  | 18                        | 4.8                                   | 5.5                            | 6   | 12                 | 18              | 0                  |
| Douglas fir .....     | 88            | 23                      | .....                                      | 23                        | .....                                 | 4.0                            | 23  | 0                  | 23              | 0                  |
| Douglas fir .....     | 93            | 25                      | .....                                      | 25                        | .....                                 | 4.0                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 94            | 25                      | .....                                      | 25                        | .....                                 | 4.0                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 95            | 25                      | .....                                      | 25                        | .....                                 | 4.0                            | 25  | 0                  | 25              | 0                  |
| Douglas fir .....     | 8             | 22                      | .....                                      | 0                         | 12.2                                  | .....                          | .....   | .....              | .....           | .....              |
| Douglas fir .....     | 18            | 24                      | .....                                      | 0                         | 17.6                                  | .....                          | .....   | .....              | .....           | .....              |
| Douglas fir .....     | 54            | 25                      | .....                                      | 25                        | .....                                 | 15.0                           | 25  | 0                  | 22              | 3                  |
| Maple, Oregon .....   | 83            | 25                      | .....                                      | 25                        | .....                                 | 5.5                            | 25  | 0                  | 25              | 0                  |
| Pine, lodgepole ..... | 99            | 25                      | .....                                      | 25                        | .....                                 | 1.9                            | 25  | 0                  | 25              | 0                  |
| Pine, lodgepole ..... | 104           | 25                      | .....                                      | 25                        | .....                                 | 1.9                            | 25  | 0                  | 25              | 0                  |
| Pine, lodgepole ..... | 50            | 25                      | 5  | 15                        | 12.8                                  | 15.4                           | 0   | 15                 | 3               | 12                 |
| Pine, lodgepole ..... | 85            | 25                      | .....                                      | 25                        | .....                                 | 3.9                            | 25  | 0                  | 25              | 0                  |
| Pine, lodgepole ..... | 86            | 25                      | .....                                      | 25                        | .....                                 | 3.9                            | 25  | 0                  | 25              | 0                  |
| Pine, ponderosa ..... | 56            | 25                      | .....                                      | 21                        | 10.7                                  | 14.3                           | 12  | 9                  | 21              | 0                  |

Table 6. CHARACTERISTICS OF TREATED FENCE POSTS  
Pressure processes

| Species                   | Series number | Number of posts in test | Post description | Sapwood              | Ground-line perimeter |                       |                       | Type of preservative treatment   |
|---------------------------|---------------|-------------------------|------------------|----------------------|-----------------------|-----------------------|-----------------------|--|
|                           |               |                         |                  |                      | Minimum               | Maximum               | Average               |  |
| Douglas fir .....         | 52            | 25                      | Square, incised  | <i>Per cent</i><br>0 | <i>Inches</i><br>16.0 | <i>Inches</i><br>16.0 | <i>Inches</i><br>16.0 | Gasco creosote oil, posts incised, absorption 4.23 pounds per post (7.6 pounds per cubic foot)                       |
| Douglas fir .....         | 45            | 25                      | Square           | 0                    | 16.0                  | 16.0                  | 16.0                  | Chemonite, average retention 0.58 pounds of dry salt per cubic foot  |
| Douglas fir .....         | 43            | 25                      | Round, peeled    | 60                   | 12.0                  | 16.7                  | 14.2                  | Chromated zinc chloride, absorption of 0.78 pounds dry salt per post (1 pound per cubic foot)                        |
| Douglas fir .....         | 7             | 25                      | Round, peeled    | 60                   | 12.0                  | 21.0                  | 17.7                  | 70 per cent creosote, 30 per cent fuel oil, absorption 1.5 to 16 pounds (average 7.2 pounds) per post, treated twice |
| Douglas fir .....         | 51            | 25                      | Square, incised  | 0                    | 16.0                  | 16.0                  | 16.0                  | Coal-tar creosote and petroleum mixture, average absorption 3.8 pounds per post, (6.2 pounds per cubic foot)         |
| Douglas fir .....         | 53            | 25                      | Square, incised  | 0                    | 16.0                  | 16.0                  | 16.0                  | Coal-tar creosote, absorption 8.1 pounds per post (13.0 pounds per cubic foot)                                       |
| Douglas fir .....         | 23            | 49                      | Round, peeled    | 60                   | 11.6                  | 16.7                  | 14.5                  | Creosote, absorption unknown   |
| Douglas fir .....         | 42            | 25                      | Square           | 0                    | 16.0                  | 16.0                  | 16.0                  | Wolman salts (Tanalith), dry salt absorption 0.302 pounds per cubic foot, kiln dried after treatment                 |
| Douglas fir .....         | 33            | 25                      | Square           | 0                    | 13.9                  | 16.6                  | 14.8                  | Zinc-meta-arsenite, absorption 0.1 pounds per post, treated twice  |
| Douglas fir .....         | 96            | 25                      | Round, peeled    | 60                   | 14.1                  | 16.9                  | 22.0                  | Boliden salts, average retention of 0.44 pound dry salt per cubic foot   |
| Douglas fir .....         | 98            | 24                      | Square           | 5                    | 14.5                  | 14.5                  | 14.5                  | Boliden salts, average retention of 0.40 pound dry salt per cubic foot   |
| Hemlock, West Coast ..... | 41            | 25                      | Square           | 0                    | 16.0                  | 16.0                  | 16.0                  | Wolman salts (Tanalith), dry salt absorption 0.302 pounds per cubic foot, posts kiln dried after treatment           |
| Hemlock, West Coast ..... | 44            | 25                      | Square           | 0                    | 16.0                  | 16.0                  | 16.0                  | Chemonite, average retention 0.75 pounds of dry salt per cubic foot  |

Table 7. SERVICE RECORDS OF TREATED FENCE POSTS  
*Pressure processes*

| Species                   | Series number | Number of posts in test | Number of posts removed at last inspection | Number of posts remaining | Average service life of removed posts | Service age of remaining posts | Location and extent of deterioration in remaining posts |                        |                        |                        |
|---------------------------|---------------|-------------------------|--|---------------------------|---------------------------------------|--------------------------------|---|------------------------|------------------------|------------------------|
|                           |               |                         |  |                           |                                       |                                | Ground-line zone  |                        | Top                    |                        |
|                           |               |                         |  |                           |                                       |                                | Little or none  | Moderate to severe     | Little or none         | Moderate to severe     |
|                           |               |                         |  |                           | <i>Years</i>                          | <i>Years</i>                   | <i>Number of posts</i>                                  | <i>Number of posts</i> | <i>Number of posts</i> | <i>Number of posts</i> |
| Douglas fir .....         | 52            | 25                      | ....                                       | 25                        | .....                                 | 15.0                           | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 45            | 25                      | 1  | 24                        | 17.4                                  | 17.4                           | 24  | 0                      | 24                     | 0                      |
| Douglas fir .....         | 43            | 25                      | ....                                       | 17                        | 11.2                                  | 17.7                           | 13  | 4                      | 17                     | 0                      |
| Douglas fir .....         | 7             | 25                      | ....                                       | 25                        | .....                                 | 25.6                           | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 51            | 25                      | ....                                       | 25                        | .....                                 | 15.0                           | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 53            | 25                      | ....                                       | 25                        | .....                                 | 15.0                           | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 23            | 48                      | ....                                       | 48                        | .....                                 | 25.4                           | 48  | 0                      | 48                     | 0                      |
| Douglas fir .....         | 42            | 25                      | ....                                       | 25                        | .....                                 | 17.8                           | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 33            | 25                      | 4  | 15                        | 20.5                                  | 21.5                           | 11  | 4                      | 15                     | 0                      |
| Douglas fir .....         | 96            | 25                      | ....                                       | 25                        | .....                                 | 1.9                            | 25  | 0                      | 25                     | 0                      |
| Douglas fir .....         | 98            | 24                      | ....                                       | 24                        | .....                                 | 1.9                            | 24  | 0                      | 24                     | 0                      |
| Hemlock, West Coast ..... | 41            | 25                      | ....                                       | 25                        | .....                                 | 17.8                           | 23  | 2                      | 25                     | 0                      |
| Hemlock, West Coast ..... | 44            | 25                      | ....                                       | 25                        | .....                                 | 17.4                           | 25  | 0                      | 25                     | 0                      |

Table 8. REMOVAL RECORDS OF UNTREATED FENCE POSTS

| Species             | Series number | Date set | Number of posts in test | Total number of posts re-removed | Number of posts removed each annual inspection year |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |     |  |  |  |  |  |
|---------------------|---------------|----------|-------------------------|----------------------------------|---|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|--|--|--|--|--|
|                     |               |          |                         |                                  | 31  | 32  | 33  | 34  | 35  | 36  | 37  | 38  | 39  | 40  | 41  | 42  | 43  | 44  | 45  | 46  | 47  | 48  | 49  | 50  | 51  | 52  | 53  | 54  |     |  |  |  |  |  |
| Alder, red          | 16            | 3- 5-29  | 25                      | 25                               | 1   | 6   | 3   | 7   | 8   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Alder, red          | 106           | 11- 5-22 | 25                      | 4                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Ash, Oregon         | 28            | 3-19-30  | 25                      | 25                               | ---   | 1   | 1   | 8   | 4   | 2   | 5   | 3   | --- | --- | --- | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Cascara             | 20            | 3- 5-29  | 12                      | 12                               | 1   | 3   | 1   | 4   | 1   | 1   | --- | --- | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Cascara             | 47            | 1-29-38  | 26                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 1   | 4   | 4   | 1   | 2   | 4   | 1   | 6   | --- | 1   | --- | --- | --- |     |  |  |  |  |  |
| Cedar, Alaska       | 46            | 11- 6-37 | 24                      | 14                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 1   | --- | --- | --- | --- |     |  |  |  |  |  |
| Cedar, incense      | 29            | 3-19-30  | 25                      | 23                               | ---   | --- | --- | 1   | 5   | --- | 1   | --- | 2   | --- | --- | 2   | 2   | --- | 3   | --- | --- | 1   | 3   | --- | 2   | 1   | --- | --- |     |  |  |  |  |  |
| Cedar, Port Orford  | 21            | 5- 4-29  | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | 1   | --- | 1   | --- | --- | 2   | --- | 2   | 3   | 10  | --- | 3   | 2   | 2   | --- |     |  |  |  |  |  |
| Cedar, western red  | 10            | 3- 6-29  | 25                      | 19                               | ---   | --- | --- | --- | --- | --- | --- | --- | 1   | --- | --- | --- | --- | 1   | --- | --- | --- | 4   | 1   | 2   | 6   | 1   | 3   | --- |     |  |  |  |  |  |
| Cedar, western red  | 11            | 4- 1-29  | 25                      | 23                               | ---   | --- | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- | 1   | 1   | 1   | 1   | --- | 3   | 1   | 3   | 4   | 5   | 2   | --- |     |  |  |  |  |  |
| Cottonwood, black   | 14            | 3- 5-29  | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Cottonwood, black   | 82            | 3-24-49  | 25                      | 17                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 3   | 9   | 6   | 5   | --- |  |  |  |  |  |
| Cypress, Arizona    | 84            | 10- 6-51 | 25                      | 9                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 1             | 1- 7-28  | 25                      | 25                               | ---   | 4   | 5   | 7   | 4   | 2   | 1   | 2   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 55            | 10-11-39 | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 1   | 6   | 2   | 7   | 2   | 4   | --- | 3   | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 57            | 12- 6-39 | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 8   | 8   | 8   | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 72            | 12-17-48 | 25                      | 12                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 97            | 11-17-52 | 25                      | 1                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Douglas fir         | 100           | 11-19-52 | 25                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Fir, grand          | 15            | 3- 5-29  | 25                      | 25                               | 1   | 4   | 1   | 3   | 2   | 1   | 3   | 1   | 2   | 1   | 3   | 1   | 2   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Hemlock, West Coast | 38            | 9-20-33  | 25                      | 25                               | ---   | --- | --- | --- | --- | 3   | 5   | 6   | 6   | 2   | --- | 1   | 1   | --- | --- | 1   | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Juniper, western    | 30            | 1-12-30  | 25                      | 17                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Larch, western      | 37            | 9-20-33  | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | 5   | 9   | 1   | 2   | 2   | 2   | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Locust, black       | 40            | 4-13-35  | 25                      | 9                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Madrone, Pacific    | 26            | 2- 6-30  | 25                      | 25                               | ---   | --- | 3   | 6   | 7   | 3   | 6   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Maple, Oregon       | 17            | 3- 5-29  | 25                      | 25                               | ---   | --- | --- | 11  | 8   | 3   | 3   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Metal, angle iron   | 60            | 11-13-48 | 25                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Metal, T-post       | 61            | 11-13-48 | 25                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Metal, H-beam       | 69            | 12-11-48 | 9                       | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Metal, channel      | 70            | 12-11-48 | 10                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Metal, T-post       | 71            | 12-11-48 | 10                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Oak, Oregon white   | 19            | 5- 7-29  | 23                      | 17                               | ---   | --- | --- | --- | --- | --- | 2   | 5   | 2   | --- | 2   | 1   | --- | --- | --- | --- | --- | 1   | 1   | --- | 1   | --- | --- | --- |     |  |  |  |  |  |
| Osage-orange        | 32            | 4-15-33  | 26                      | 0                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, lodgepole     | 48            | 11- 1-38 | 26                      | 26                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 4   | 7   | 6   | 5   | 1   | 1   | 1   | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, lodgepole     | 49            | 11- 1-38 | 25                      | 25                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | 7   | 11  | 6   | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, lodgepole     | 103           | 11-15-52 | 25                      | 6                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, ponderosa     | 36            | 9-20-33  | 25                      | 25                               | ---   | --- | --- | --- | --- | 1   | 3   | 7   | 7   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, sugar         | 35            | 9-20-33  | 25                      | 25                               | ---   | --- | --- | --- | --- | 2   | 2   | 8   | 3   | 2   | 2   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, sugar         | 34            | 9-20-33  | 25                      | 25                               | ---   | --- | --- | --- | --- | 1   | 2   | 7   | 11  | 3   | --- | --- | --- | 1   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Pine, Idaho white   | 58            | 12-20-39 | 25                      | 2                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Redwood             | 31            | 4-15-33  | 26                      | 26                               | ---   | --- | --- | --- | --- | 4   | 10  | 2   | 1   | 4   | 5   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Sitka               | 76            | 10- 6-51 | 25                      | 7                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Tanoak              | 13            | 3- 5-29  | 23                      | 11                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Yew, Pacific        | 76            | 10- 6-51 | 25                      | 7                                | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |
| Yew, Pacific        | 13            | 3- 5-29  | 23                      | 11                               | ---   | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- | --- |     |  |  |  |  |  |

Table 9. REMOVAL RECORDS OF TREATED FENCE POSTS  
*Nonpressure processes*

[illegible]



Table 10. REMOVAL RECORDS OF TREATED FENCE POSTS  
*Pressure processes*

[illegible]

## T. J. Starker Post Farm Cooperators

- Anaconda Copper Mining Co., Wood Preserving Department, Butte, Montana  
Bolidens Gruvaktiebolag, Stockholm, Sweden  
Bradley-Woodard Lumber Co., Bradwood, Oregon  
Carbolineum Wood Preserving Co., Milwaukee, Wisconsin  
Chemonite Wood Preserving Co., San Francisco, California  
J. W. Copeland Yards, Corvallis, Oregon  
Corvallis Lumber Co., Corvallis, Oregon  
Harold Dahl, Troutdale, Oregon  
Dant & Russell, Portland, Oregon  
Dow Chemical Co., Midland, Michigan  
Holmes-Eureka Lumber Co., Eureka, California  
The Hunt Co., 3700 West Six Mile Road, Detroit, Michigan  
C. D. Johnson Lumber Corp., Toledo, Oregon  
Kirchmann Hardwood Co., San Francisco, California  
McGoldrick Lumber Co., Spokane, Washington  
Nuodex Products Co., Inc., Elizabeth, F, New Jersey  
Osmose Wood Preserving Co. of America, Inc., Buffalo, New York  
Pope & Talbot, Inc., St. Helens, Oregon  
Portland Gas & Coke Co., Portland, Oregon  
R. H. Rawson, Portland, Oregon  
Southern Pacific Co., Eugene, Oregon  
U. S. Department of Agriculture, Forest Service  
    Deschutes National Forest, Bend, Oregon  
    Forest Products Laboratory, Madison, Wisconsin  
    Pacific Northwest Forest and Range Experiment Station, Portland, Oregon  
    Umpqua National Forest, Roseburg, Oregon  
    Willamette National Forest, Eugene, Oregon  
Warren Southwest, Inc., Wilmington, California  
Washington Wood Preserving Co., Spokane, Washington  
West Coast Wood Preserving Co., Seattle, Washington  
West Oregon Lumber Co., Portland, Oregon  
Western Pine Association, Portland, Oregon  
Weyerhaeuser Timber Co., Klamath Falls, Oregon  
Willamette Valley Lumber Co., Dallas, Oregon